

## 6FM75TE 12V 75Ah(10hr)

The rechargeable batteries are lead-lead dioxide systems. The dilute sulfuric acid electrolyte is absorbed by separators and plates and thus immobilized. Should the battery be accidentally overcharged producing hydrogen and oxygen, special one-way valves allow the gases to escape thus avoiding excessive pressure build-up. Otherwise, the battery is completely sealed and is, therefore, maintenance-free, leak proof and usable in any position.

### Battery Construction

Component	Positive plate	Negative plate	Container	Cover	Safety valve	Terminal	Separator	Electrolyte
Raw material	Lead dioxide	Lead	ABS	ABS	Rubber	Copper	Fiberglass	Sulfuric acid


### General Features

- Absorbent Glass Mat (AGM) technology for efficient gas recombination of up to 99% and freedom from electrolyte maintenance or water adding.
- Not restricted for air transport-complies with IATA/ICAO Special Provision A67.
- UL-recognized component.
- Can be mounted in any orientation.
- Computer designed lead, calcium tin alloy grid for high power density.
- Long service life, float or cyclic applications.
- Maintenance-free operation.
- Low self discharge.

### Dimensions and Weight

Length(mm / inch)	258 / 10.2
Width(mm / inch)	168 / 6.61
Height(mm / inch)	211 / 8.31
Total Height(mm / inch)	230.5 / 9.07
Approx. Weight(Kg / lbs)	21.2 / 46.7

\* Weight deviation:  $\pm 3\%$



### Performance Characteristics

Nominal Voltage	12V
Number of cell	6
Design Life	10 years
Nominal Capacity 77°F(25°C)	
10 hour rate (7.5A, 10.8V)	75Ah
5 hour rate (13.5A, 10.5V)	67.5Ah
1 hour rate (46.5A, 9.6V)	46.5Ah
Internal Resistance	
Fully Charged battery 77°F(25°C)	$\leq 7.0$ mOhms
Self-Discharge	
3% of capacity declined per month at 20°C(average)	
Operating Temperature Range	
Discharge	-20~60°C
Charge	-10~60°C
Storage	-20~60°C
Max. Discharge Current 77°F(25°C)	700A(5s)
Short Circuit Current	1800A
Charge Methods: Constant Voltage Charge 77°F(25°C)	
Cycle use	2.40-2.45VPC
Maximum charging current	22.5A
Temperature compensation	-30mV/°C
Standby use	2.20-2.28VPC
Temperature compensation	-20mV/°C

### Discharge Constant Current (Amperes at 77°F25°C)









End point Volts/cell	10min	15min	30min	45min	1h	3h	5h	10h
1.60V	136	105	77.0	58.0	46.5	19.0	14.2	7.58
1.65V	130	100	74.8	56.0	45.0	18.9	14.0	7.56
1.70V	124	96.0	72.9	54.4	43.5	18.9	13.8	7.54
1.75V	115	91.5	70.0	53.0	41.7	18.8	13.5	7.52
1.80V	110	88.0	67.0	51.0	40.0	18.8	13.3	7.50

### Discharge Constant Power (Watts at 77°F25°C)

End point Volts/cell	10min	15min	30min	45min	1h	2h	3h	5h
1.60V	261	203	148	111	89.8	54.1	37.5	26.6
1.65V	250	194	143	107	86.5	52.6	37.0	26.4
1.70V	238	187	139	102	84.2	51.6	36.8	26.2
1.75V	226	180	135	98.0	80.0	50.1	36.3	26.0
1.80V	215	170	129	94.0	77.5	48.5	36.0	25.8

(Note)The above characteristics data are average values obtained within three charge/discharge cycles not the minimum values.

All data shall be changed without notice, Vision reserves the right to explain and update the information contained hereinto.



ISO9001:2008

MH25860

G4M19906-9202-E-16

[www.vision-batt.com](http://www.vision-batt.com)

**Shenzhen Center Power Tech. Co., Ltd.**  
 Center Power Industrial Park, Tongfu Industrial District Dapeng Town, 518120 Shenzhen, China  
 Tel: (+86-755) 8431 8088 Fax: (+86-755) 84318038 E-mail: sales@vision-batt.com